Technical Data Sheet

Protecflam Industries
Edition 30/06/2026

Verniflam® F4X

Finishing coating for wood and wood-based materials

Description

Verniflam® F4X is a water borne top coating for **Verniflam® AL20X** intumescent paint, for timber fire protection that can be used indoor and outdoor.

Before use, please contact Protecflam Industries to make sure the product is suitable for your needs.

Fire reaction class

Verniflam® F4X alone is a non-degrading coating, according to fire reaction regulations.

Used as top-coat of Verniflam® AL20X intumescent paint , Class B-s1-d0 reaction to fire to any wooden substrate having density 390 kg/m3 or above

Classification Report: 0944/DC/REA/16_3 (EN 13823, EN ISO 11925-2)

Color & conditioning

White mat. Other colors on request.
4 kg cans.

- Opaque white
- Matt finish
- 5 kg cans

On-request colors: contact us

- Translucent
- Matt finish
- 4,25 kg cans

On-request colors: contact us

Storage

Store in a cool dry and shaded place, protected from direct sunlight up to 18 months from the production date. The storage temperature should be between +10 °C et +25 °C:

Protect from freezing!

protecflam

Protecflam Industries
31, rue de l'Etoile du Matin
FR- 44600 Saint Nazaire
www.protecflam.fr
contact@protecflam.com
+33(0)2 40 90 10 80

Technical Data Sheet

Technical data

Density:	approx. 1,10 g/cm³ (20°C)
Solids content (weight):	33 to 37 g/L.
V.O.C.:	< 35 g/L
Spreading rate:	approx. 60 g/m² (indoor) approx. 120 g/m² (outdoor, with top-coat F4X)
Drying time:	at +20°C, RH 55%: touch dry after 30 minutes. Ready for overcoating after 16 to 24 hours. Drying time may vary according to wet film thickness and relative humidity of the drying room.

Before use

Timber pieces must be dry and cleaned from dust, paint, wax, dirt, resin etc.

Use a sanding machine if needed.

Timber humidity must not exceed 12%, temperature should be between +5°C and +30°C.

Air relative humidity must not exceed 70%.

Instructions for use

Stirring

Stir well until the product is homogeneously consistant and without lumps. Use a low-speed mechanical display if needed.

Coating

Product can be applied with a brush, a roller or a spray gun at 60 to 120 g/m² (depending on the use, see above spreading rates) in two coats. Water may be added (5 to 10 %); adjust spreading rates accordingly.

Thinner

Water or neutral detergent. Rinse and clean tools immediately after work.

protecflam

Protecflam Industries
31, rue de l'Etoile du Matin
FR- 44600 Saint Nazaire
www.protecflam.fr
contact@protecflam.com
+33(0)2 40 90 10 80

Other

Between two coats, gently sand the surfaces using 120-grit abrasive paper.

Measured values

All the values included in this technical sheet have resulted from laboratory tests. Deviations from standard values may occur.

Safety

For additional safety information, please read the Material Safety Data Sheet at Protecflam Industries.

protecflam

Protecflam Industries
31, rue de l'Etoile du Matin
FR- 44600 Saint Nazaire
www.protecflam.fr
contact@protecflam.com
+33(0)2 40 90 10 80